




### General data

Panel	1820 x 145
Total thickness	12,5 mm
Numbers of panels per pack	6
Nested Lengths	Max. 1 plank out of 6
m² per pack	1,583 m²
Kg per pack	17,2 kg

### Panel build up

Toplayer	PEFC controlled sources	EN 13489	± 2,5 mm
Core board	PEFC controlled sources		HDF Mastercore
Backing layer	PEFC controlled sources	Wood Veneer	2 mm
Tongue and groove	Length		Uniclic
	Width		Uniclic Multifit



### Warranty

Domestic use	Conditions in each pack	33 years
Uniclic - Multifit connection		Lifetime
Commercial		On request

"Wood for Life" Edge Protect + Provides a warranty on build-up of residue dirt along the edges due to maintenance over the years 10 years

"Wood for Life" Surface & Edge Protect + (lacquered products only) Provides a warranty on pollution of surface structure and a warranty on build-up residue dirt along the edges due to maintenance over the years 10 years

### Surface layer

Wood species	Oak
Origin	Europe
Finishing	UV cured Oiled finish
	UV cured Lacquer
	Anti-scratch top coat
Natural variance	Due to nature, visual surface can deviate from samples
Surface treatments	cf catalogue/website

### Grading

According to EN 13489:2002 Free Class

	According to EN 13469:2002 Free Class		
	Nature	Marquant	Vibrant
	Face of the element		
Sound sapwood	Permitted, colour stained	Permitted, colour stained	Permitted, colour stained
Knots	Permitted if max 20 mm fully filled	Permitted if max 50 mm half or fully filled	Permitted if max 80 mm half or fully filled
Checks/Cracks	Not permitted	Permitted if Closed Crack ≤ 1/2 of the plank	Permitted unlimited
Bark pockets	Not permitted	Not permitted	Not permitted
Lightning shake	Not permitted	Not permitted	Not permitted
Grain structure	Grain width ≤ 80 mm	Unlimited	Unlimited
Sound heart	Permitted	Permitted	Permitted
Colour variation	Mild natural variation	Lively variation	Very lively variation
Stick marks	Not permitted	Not permitted	Not permitted
Medullary ray	Permitted	Permitted	Permitted
Biodeterioration	Not permitted	Not permitted	Not permitted
	Non-visible parts		
All features permitted without any limitation as to size or quantity if these do not impair the strength or wearing quality of the parquet flooring			

Installation		Norm requirements	
Floating		On Quick-Step underlay	cf installation instructions
Glued to subfloor		Quick-Step MS polymer resin	cf installation instructions
General aspect of installed flooring	EN 13489	Lipping - difference in height (mm)	≤ 0,20
		difference in width (mm)	≤ 0,20
		cupping lengthwise %	≤ 0,1
		cupping in width %	≤ 0,2
Dimensional stability	ISO 24339	Cupping short side max %	≤ 0,30
	Changes 30 - 85 % RH	Cupping short side min %	≥ - 0,20
		Open joints short side (mm)	≤ 0,20
		Open joints long side (mm)	≤ 0,30
Underfloor heating	Suitable	cf special installation instructions	
Classification properties			
Wear resistance	SIS 923509	Falling sand	800 - 1000
	DIN 68861	S33	100 - 1050
Stain resistance	EN 13442		class 3
		Floors with "Wood for Life" Surface Protect + (Lacquered only)	class 5
CE	EN 14342:2013	notified body	0766 EPH Dresden
Castor chairs	ISO 4918	Tested with underlay	DOP: On pack 25.000
Slip resistance	CEN/TS 15676 : 2008	Dry Pendulum test	Depending on structure and surface treatment
USRV 37-57			
Emission of formaldehyde	EN 717-1		≤ E1
PCP	CEN/TR 14823:2004		≤ 5 ppm
Heat resistance	EN12664:2001		0,11 m².K/W
Reaction to fire	EN 13501-1		Cfl-s1
Ecological certificates			
AFFSET	A	France	
PEFC	PEFC/07-32-37		
EPD	On request		
Higieniczny	HK/B/0149/03/2017	Poland	

